



## MagnaPrint® Bling Range

## **Ready to use Metallic Printing Pastes**

MagnaPrint® Bling products are a ready to use metallic print pastes that has excellent shine and elasticity.

The range consists of the following products:

MagnaPrint® Bling Silver MagnaPrint® Bling Gold MagnaPrint® Bling Bronze

## **Application**

MagnaPrint® Bling products should be printed through a 3261 (86 Œ156) mesh screen with rectangular profile squeegees. As the particle size is 10-60 micron this should be considered when selecting screen mesh.

When printing as part of a multicoloured design print the MagnaPrint® Bling products as the last screen to avoid pick up.

After printing the garment/panel should be cured, ideally for 21/23 minutes @165°C (330°F).

## **SPECIFICATION**



**FABRIC TYPES** Cotton / Poly Cotton Blends



**MESH** 32 - 61T (86 - 156) Mesh



**SQUEEGEE** Medium 65 Shore Rectangular



**STENCIL** Water resistant emulsion



**CURE TEMPERATURE**  $2^{1}/_{2}$  - 3 Minutes at 165°C (330°F)



**PIGMENT LOADING** Up to 6% MagnaPrint® Eco **Pigments** 



**ADDITIVES** Retardant Gel, Crosslinker DO, Softener TS Conc



**STORAGE** In cool place properly closed:



**HEALTH & SAFETY** MSDS available upon

>5c (40F) <25c (77F)

request



**CLEAN UP** Wash off screen using water and mild detergent

All information is given in good faith butwithout warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.

E: info@magnacolours.com

Company registered in England No. 01378495, VAT No. GB 997 3172 70

